

	Relative Humidity									
	10%	20%	30%	40%	50%	60%	70%	80%	90%	100%
Air Temp (F)	Dew Point (Concrete Surface Temperature)									
<b>40</b>	5	8	14	18	24	28	31	34	37	40
<b>45</b>	5	9	16	23	28	32	36	39	42	45
<b>50</b>	6	13	21	27	33	36	40	44	47	50
<b>55</b>	8	16	25	31	36	41	45	49	52	55
<b>60</b>	9	20	29	35	41	46	50	54	57	60
<b>65</b>	10	24	33	40	48	51	55	58	62	65
<b>70</b>	13	28	37	45	50	55	60	64	67	70
<b>75</b>	17	31	42	49	55	60	64	68	72	75
<b>80</b>	20	35	46	53	60	65	69	73	77	80
<b>85</b>	24	40	50	58	64	69	74	78	82	85
<b>90</b>	27	43	54	62	69	74	79	83	87	90
<b>95</b>	30	48	59	67	73	79	84	88	92	95
<b>100</b>	34	52	62	71	78	83	88	93	97	100
*Dew Point is the temperature at which water forms on a surface										
*Coatings should not be applied if air or surface temp is within 5 degrees above dew point										